



No. 1364563.5

(Please quote this number in all correspondence)

CLIENT: Textilia Ltd.
PO Box 37 378
Parnell, Auckland
Attn.: Therese Ronalde

SAMPLE RECEIVED FROM: Textilia Ltd.

Date Received: 8.3.21

SAMPLE DESCRIPTION:
Upholstery woven fabric – Precinct
Colour – Sector
Nominal Composition – 78% Recycled Polyester 22% Polyester
Nominal Weight – 389 grammes per lineal metre.

Client Order No.: Client Reference: 1 of 3

**AS/NZS 1530.3 – 1999 Methods for Fire Tests on Building Materials, Components and Structures
Part 3: Simultaneous Determination of Ignitability, Flame Propagation,
Heat Release and Smoke Release**

Note: This test was sub-contracted (Test No. 21-001171).
Face Tested: Face

	Standard Error	Mean	
Ignition Time	0.24	8.26 min.	
Flame Propagation Time	Nil	Nil sec.	
Heat Release Integral	2.7	72.2 kJ/m ²	
Smoke Release, log d	0.0119	-0.8006	
Optical Density, d		0.1586/metre	
Number of Specimens Ignited		6	
Number of Specimens Tested		6	
Regulatory Indices:			
Ignitability Index		12	Range 0-20
Spread of Flame Index		0	Range 0-10
Heat Evolved Index		2	Range 0-10
Smoke Developed Index		5	Range 0-10

“THIS REPORT APPLIES ONLY TO THE SAMPLES TESTED”
Samples and their identifying descriptions have been provided by the client unless otherwise stated. NZWTA Ltd makes no warranty, implied or otherwise as to the source of the tested samples. The above results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY. This document shall not be reproduced except in full.

L A Greer
Signatory


C Judan
Signatory

18/03/2021



No. 1364563.5

(Please quote this number in all correspondence)

CLIENT: Textilia Ltd. PO Box 37 378 Parnell, Auckland Attn.: Therese Ronalde	SAMPLE RECEIVED FROM: Textilia Ltd. SAMPLE DESCRIPTION: Upholstery woven fabric – Precinct Colour – Sector Nominal Composition – 78% Recycled Polyester 22% Polyester Nominal Weight – 389 grammes per lineal metre.	Date Received: 8.3.21
---	--	------------------------------

Client Order No.:	Client Reference:	2 of 3
--------------------------	--------------------------	--------

The reaction of thin unsupported flexible materials to flame impingement can be assessed in accordance with AS 1530.2. Where materials of thickness less than 2mm that are sufficiently flexible to be bent by hand around a mandrel of 2mm diameter or less are subjected to the test described herein, they should also be subjected to the test in AS 1530.2.

Each test specimen had an unattached backing of 4.5mm thick fibre reinforced cement board.

The specimens melted away from the area of maximum heat and produced flaming droplets during the test. Due to this phenomena it should be recognised that this test result may not be a true indication of the product's fire hazard properties.

The specimens melted and flowed away from the area of maximum heat and produced flaming droplets during the test. Due to this phenomena it should be recognised that this test result may not be a true indication of the product's fire hazard properties.

Each test specimen was restrained on the exposed face by a layer of galvanised welded square mesh made from wire of nominal diameter 0.8mm and nominal spacing 12mm in both directions and securely fixed to a backing board at four points each 100mm from the centre of the sample and the assembly clamped in four places.

To allow free movement of the sample during testing all corners were folded away from the clamps.

"THIS REPORT APPLIES ONLY TO THE SAMPLES TESTED"

Samples and their identifying descriptions have been provided by the client unless otherwise stated. NZWTA Ltd makes no warranty, implied or otherwise as to the source of the tested samples. The above results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY. This document shall not be reproduced except in full.

L A Greer
Signatory


C Judan
Signatory

18/03/2021

New Zealand Wool Testing Authority Ltd

22 Bridge Street, PO Box 12055

Ahuriri, Napier 4144, New Zealand

T +64 6 835 1086, F +64 6 835 6473 Email: testing@nzwta.co.nz